



PRODUCTS INFO SHEET

Product	Clear Guard	Premier Flow	Crystal Cast
Mixing Ratio by Volume	1:1 (A:B)	1:1 (A:B)	<i>We are still formulating this product!</i>
Mixing Ratio by Weight	100:83 (A:B)	100:83 (A:B)	N/A
Mixed Viscosity	1300cps	1200cps	N/A
Max Recommended Pour Depth	1/8 inch per layer	1/2 inch per layer	N/A
Pot Life	45 minutes	45-50 minutes	N/A
Tack-free Time	4-6 hours	6-8 hours	
Cure Time	24 hours	24 hours	N/A
Shore Hardness Scale (after 7 day cure)	D85	D78	N/A
Low VOC	Yes	Yes	N/A
UV Resistant	Yes	No	
Ideal Working Environment	72-78°F	72-78°F	N/A
Max Intermittent Temp. Resistance	Up to 300°F	Up to 300°F	N/A
Max Sustained Temp. Resistance	Up to 165°F	Up to 165°F	N/A
Shelf Life	12 months	12 months	N/A
Ideal Applications	Tabletops, countertops, bartops, crafts, art, & more	Coatings, Shallow Castings, Crafting, Arts & More	N/A